



Date, 28<sup>th</sup> January, 2008  
TR n° 046-bis/2008  
Ref. E-Mail dated 18.12.2007

To  
MERLETT TECNOPLASTIC S.p.A.  
Via XXV Aprile, 16  
21020 DAVERIO (VA)

Received 22.01.2008

Start tests 23.01.2008

End tests 23.01.2008

Page 1 of 1

## T E S T R E P O R T

**Subject:** DETERMINATION OF BURNING BEHAVIOUR OF A SAMPLE OF RIGID PVC SUPPLIED AS SHEETS 140x80x5 mm

**SAMPLE**

**Type of material**  
**Spiralina Merlett (08)**  
**(RIGID PVC)**

**Test Method**

**Burning rate**  
(Test pieces 138x80x5 mm)

mm/min

0

UNI ISO 3795

**Remark:** The flame extinguishes before reaching the first measuring.

The contained results refer only to the tested sample.

-----  
This report cannot be partially reproduced without the laboratory approval.

  
L. Lamboglia, *Operator*

  
F. Casa, *Director*